

"Effect of absorbing impurities on explosive initiation by laser light." Combustion, Explosion, and Shock Waves 25.1 (1989): 1-7.  
"Effect of Additives of Ultrafine Carbon Particles on the Laser Initiation Threshold of a Polymer-Photosensitive Explosive Composition." Khim. Fiz 24.10 (2005): 49-56.  
"Initiation of Tetranitropentaerythrit by Millisecond Laser Pulses." Russian Physics Journal 56.12 (2014): 1357-1362.

K doped with Resonant Hollow Gold Nanoshells. No. LLNL-CONF-656673. Lawrence Livermore National Laboratory (LLNL), Livermore, CA, 2014.

The influence of aluminum powder dispersity on composite solid propellants ignitability by laser radiation."Combustion and Flame

with nanoaluminum additives under the influence of laser radiation."Russian Journal of Physical Chemistry

sensitivity to the laser effect through the influence of pulsed laser radiation at different wavelengths."Russian Journal of Physical Chemistry B 8.3 (2013): 453-456.

by opaque film coating //Combustion and Flame 172 (2016): 215-221.

## TETRANITRATE BY NANOSECOND PULSES

ft. A.G. Krechetov, A.V. Tupitsyn

Novosibirsk, Russia

olve a wide range of tasks, from medical use. The issue of energetic ion. Presence of sensitive energetic material. Therefore, search for ways to use rest for research. Laser initiation of energetic material. Examples of such additives are metal powders [4,5,6,7].Initiation of explosive decomposition of PETN with nanoaluminum additives under the influence of pulsed laser radiation at different wavelengths."Russian Journal of Physical Chemistry B 8.3 (2013): 352-355.

tetrinitrate (PETN) initiation due to quasi-continuous fiber ytterbium laser. It was found that nanosized aluminum, and coating thickness energy density of composites with concentrations from 0.01 to 1 decreases the threshold ignition energy as a function of the light absorbing coating layer thickness was studied. It has been found that the exothermic reaction zone formation does not always lead to the initiation of the entire sample. An analytical model describing the initiation of the exothermic decomposition reaction in the surface layer of the sample was developed. The effectiveness of the initiation of the explosion decreases with the increase in the thickness of the absorbing layer.

energy threshold at high concentrations of the additive due to the increase in the extinction index decreases the thickness of ignited layer to a value insufficient to initiate the entire sample. It has also been found to influence of method of homogenization on the ignition threshold energy by nanosecond laser pulses composites containing carbon black.

Laser ignitability of a two-component system constituted of a copper (II) oxide layer and a PETN tablet was studied [8]. An ytterbium fiber laser with 1070 nm wavelength, 20 ms pulse duration and 3.6 kW/cm<sup>2</sup> power density was used. The threshold of launching of exothermic reaction as a function of the light absorbing coating layer thickness was studied. It has been found that the exothermic reaction zone formation does not always lead to the initiation of the entire sample. An analytical model describing the initiation of the exothermic decomposition reaction in the surface layer of the sample was developed. The effectiveness of the initiation of the explosion decreases with the increase in the thickness of the absorbing layer.

### References

1. Aleksandrov, E. I., A. G. Voznyuk, and V. P. Tsipilev. "Effect of absorbing impurities on explosive initiation by laser light." Combustion, Explosion, and Shock Waves 25.1 (1989): 1-7.
2. Ilyushin, M. A., et al. "Effect of Additives of Ultrafine Carbon Particles on the Laser Initiation Threshold of a Polymer-Photosensitive Explosive Composition." Khim. Fiz 24.10 (2005): 49-56.
3. Aluker, É. D., et al. "Initiation of Tetranitropentaerythrit by Millisecond Laser Pulses." Russian Physics Journal 56.12 (2014): 1357-1362.
4. Wilkins, P. R. Laser Deflagration-to-Detonation in Keto-RDX doped with Resonant Hollow Gold Nanoshells. No. LLNL-CONF-656673. Lawrence Livermore National Laboratory (LLNL), Livermore, CA, 2014.
5. Arkhipov, Vladimir A., and Alexander G. Korotikh. "The influence of aluminum powder dispersity on composite solid propellants ignitability by laser radiation."Combustion and Flame 159.1 (2012): 409-415.
6. Aduev, B. P., et al. "Explosive decomposition of PETN with nanoaluminum additives under the influence of pulsed laser radiation at different wavelengths."Russian Journal of Physical Chemistry B 8.3 (2013): 453-456.
7. Aduev, B. P., et al. "Controlling pentaerythrite tetrinitrate sensitivity to the laser effect through the addition of nickel and aluminum nanoparticles." Russian Journal of Physical Chemistry B 8.3 (2014): 352-355.
8. Mitrofanov A. et al. Sensitization of PETN to laser radiation by opaque film coating //Combustion and Flame 172 (2016): 215-221.

## ЗАТУХАНИЕ ДЕТОНАЦИИ ЗА ФРОНТОМ УДАРНОЙ ВОЛНЫ В ПЛАСТИЧНОМ ВВ НА ОСНОВЕ ТЭНА

A.O. Кацкаров<sup>1,2</sup>, Э.Р. Прруэл<sup>1,2</sup>, К.А. Тен<sup>1</sup>, К.Н. Панов<sup>3</sup>, В.Б. Титова<sup>3</sup>, И.А. Спирин<sup>3</sup>

<sup>1</sup>Институт гидродинамики им. М.А. Лаврентьева СО РАН, г. Новосибирск, Россия

<sup>2</sup>Новосибирский государственный университет, г. Новосибирск, Россия

<sup>3</sup>РФЯЦ-ВНИИЭФ, г. Саров, Россия

В работе исследовалось взаимодействие ударной и детонационной волн в зарядах пластичного взрывчатого вещества на основе тэна. Активный слой ВВ нагружался косой ударной волной, затем, в ту же сторону вдоль слоя, направлялась

детонационная волна. Временной интервал между волнами задавался геометрией экспериментальной сборки в пределах нескольких микросекунд.

Для регистрации процесса взаимодействия волн применялся метод скоростной диагностики быстропротекающих процессов с помощью синхротронного излучения на базе ускорителя ВЭПП-3 ИЯФ СО РАН [1, 2]. Метод позволяет получить динамику процесса в виде рентгеновского щелевого кино с пространственным разрешением до 0.1 мм. Интервал между кадрами в настоящей работе 0.496 мкс, время экспозиции около 1 нс.

Было получено, что, при небольшом интервале между волнами, детонационная волна распространяется вслед за ударной без наблюдаемого изменения скорости. Увеличение временного зазора приводит к переходному процессу затухания детонации и падению скорости волны до 2.5 км/с.

#### Литература

1. Опыт применения синхротронного излучения для исследования детонационных процессов. В. М. Титов, Э.Р. Пруузэл, К.А. Тен и др. //Физика горения и взрыва. № 6. 2011. С. 3–15.
2. Э.Р. Пруузэл, К.А. Тен, Б.П. Толочко и др. Реализация возможностей синхротронного излучения в исследованиях детонационных процессов // Доклады Академии наук. Техническая физика. 2013. Т. 448. № 1. С. 38–42.

## К ВОПРОСУ О ВОЗБУЖДЕНИИ ВЗРЫВНЫХ ПРЕВРАЩЕНИЙ В ЗАРЯДАХ ВВ ПРИ ПРОНИКАНИИ В НИХ УДАРНИКОВ

И.Ф. Кобылкин

МГТУ им. Н.Э. Баумана, г. Москва, Россия

Механизмы возбуждения взрывных превращений в зарядах ВВ, заключенных в прочные металлические оболочки, при воздействии высокоскоростных ударников достаточно подробно рассмотрены в книге [1]. Там же приведены соотношения, позволяющие оценивать параметры ударного воздействия, необходимые для возбуждения различных режимов взрывного превращения на ударно-волновой стадии взаимодействия ударника с экранированным зарядом ВВ и на стадии пробития экрана. В [1] также экспериментально показано, что и при последующем проникании ударника в заряд ВВ возможно возбуждение взрывных превращений в ВВ, даже если исключить разогрев ВВ и ударника на стадии пробития оболочки. В настоящей работе предлагается феноменологическая модель процесса возбуждения взрыва в зарядах ВВ при проникании в них ударников с относительно небольшими скоростями до нескольких сотен метров в секунду. Предлагаемая модель основана на положениях теории механической чувствительности твердых ВВ [2] и теории проникания недеформируемых тел в прочные среды [3].

В соответствии с универсальным законом сопротивления давление сопротивления прониканию может быть определено с помощью соотношения

$$p = 3\sigma_{\text{пр}} + \chi\rho u^2,$$

где  $\sigma_{\text{пр}}$  – предел прочности среды на сжатие;  $\chi$  – коэффициент сопротивления головной части ударника: для полусферической головной части  $\chi = 0,5$ , для плоской  $\chi = 1$ ;  $\rho$  – плотность среды;  $u$  – скорость проникания.

Источником разогрева вытеснения ВВ из под днища в соответствии с теорией метода плавления ВВ является плавление ВВ в области плавления  $T_{\text{пл}}$ . Но сама температура плавления эта зависит от времени пребывания в области плавления, где  $T_{\text{пл}0}$  – исходная температура критической температуре  $T_c$  превращения, в [2] приходит

Поскольку для большинства следует ожидать величины  $k$

Приравнивая критическую проникания, получим соотношение икр ударника в Е

Условием необходимым для проникания в него ударника количественной оценки икр Напряжение разрушения при небольших размерах по поражающим зарядов ВВ в виде тонких слоев больше и изменяется в пределах 100–200 МПа. Поскольку проникание ударника для оценки величины икр I

акр I = 640 м/с. Кроме сжатия до края необходимо разогреть до края вытесняемого объема ВВ молния при проникании совершает ударника. В соответствии с пластическим деформированием. Вытесняемый объем равен  $S_t$  записать

где  $C$  – теплоемкость ВВ;  $S_t$  – среднее приращение температуры распределение температуры линейным, то максимальное превосходить  $\Delta T_{\text{ср}}$ . Из расчета среднего приращения

$\Delta T_{\text{ср}} = \rho S / \rho C S_t$ . Для ударника с плоским торцом к критическому и подставляя в