

Transmission electron microscopy of detonation carbon.
Photoalbum.

Trotyl (TNT)
Trotyl/hexogen (TNT/RDX 50/50)
Triaminotrinitrobenzene (TATB)
Benzotrifuroxan (BTF)

Kashkarov A.O., Pruvuel E.R., Ten K.A., Zubkov P.I.

Lavrentyev Institute of Hydrodynamics of SB RAS
Syberian Branch of Russian Academy of Science

February 9, 2016

Contents

1	Trotyl	4
2	Trotyl. Combustion products.	8
3	TNT/RDX (50/50)	10
4	TATB	16
5	BTF pressed	22
6	BTF pressed. Annealed at a temperature of 460 °C	30
7	BTF pressed. Annealed at a temperature of 515 °C	34
8	BTF plastified	38
9	BTF plastified. Annealed at a temperature of 520 °C	46






1 Trotyl



Cast charge



Diameter 20 mm

Mass: 20 g.












2 Trotyl. Combustion products.

Combustion products at atmospheric pressure.








3 TNT/RDX (50/50)



Cast charge



Diameter 20 mm



Mass: 15.5 g.



















4 TATB



Diameter 20 mm.



Mass: 22 g




















5 BTF pressed



Density: 1.80 g/cc



Mass: 17 g




























6 BTF pressed. Annealed at a temperature of 460 °C



Density: 1.80 g/cc

Mass: 17 g














7 BTF pressed. Annealed at a temperature of 515 °C



Density: 1.80 g/cc

Mass: 17 g














8 BTF plastified



Density: 1.66 g/cc



Mass: 17 g























9 BTF plastified. Annealed at a temperature of 520 °C

Density: 1.66 g/cc

Mass: 17 g

